



**Determination of Selected Material
Properties of Castable Thin Film Polyimides
for Applications in
Solar Thermal Propulsion**

By

James Patrick Paxton

**Undergraduate
Senior Year**

**Mechanical and Aerospace Engineering Department
University of Alabama in Huntsville
Huntsville, Alabama**

Presented to

**The AIAA Southeastern Regional Student Conference
April 7 - 8, 1994
Huntsville, Alabama**



This Study Will...

- Provide an Introduction to Typical Applications of Thin Film Polyimides
- Introduce 6FDA + APB Polyimides as an Important Component in Solar Thermal Propulsion
- Show Unique Methods in the Determination of Selected Material Properties of 6FDA + APB Polyimides
- Provide Modulus of Elasticity and Coefficient of Thermal Expansion Data for 6FDA + APB Polyimides



What is a Thin Film?

- Thin Sheet of a Polymer Material
- Typically .0005 - .002 Inches Thick
- Used for Stretched Membrane Mirrors and Parabolic Concentrators
- Examples of Thin Film Materials
 - Mylar™ Polyester Film
 - Kapton™ Polyimide Film
 - 6FDA + APB Polyimide Film




An Application of Thin Film Polyimides

- **Solar Thermal Propulsion is Fast Becoming an Attractive Option
for On-orbit Satellite Maneuvers**
 - LEO to GEO Orbit
 - High Performance (Typical Isp – 600 - 1000 sec.)
 - Lightweight
- **The Components of a Solar Powered Rocket Include...**



Typical Solar Thermal Rocket Configuration

SRS Proprietary



SRS Proprietary

940329Ae1409-i3.0c Ae(08) 03-29-94



Benefits of 6FDA + APB Thin Films

- Lightweight
- Optically Transparent
- Stowable / Deployable
- Superior Material Properties
- Wide Temperature Range (-450 – 750°F)
- Castable on Curved Surfaces



Design Parameters for Articles Constructed with Thin Film Polyimides


- External Loads / Pressures
- Environmental Conditions
- Transparency
- Material Properties
 - Modulus of Elasticity
 - Coefficient of Thermal Expansion
 - Coefficient of Moisture Expansion
 - Poisson's Ratio



Theory

- Modulus of Elasticity (Young's Modulus) is given by Hooke's Law

$$\sigma = E\epsilon \quad (\text{psi})$$



- Coefficient of Thermal Expansion is given by


$$\text{CTE} = \frac{\Delta L}{L \Delta T} \quad (\text{in}/(\text{in}^\circ\text{F}))$$




Thin Film Test Apparatus

- **Conforms to ASTM Standards**
- **Includes Temperature Chamber**
- **Provides Constant Uniform Loading**
- **Incorporates Unique Toggle Grip Design**
- **Computer Data Acquisition System**

Uniaxial Test Apparatus




940328Ae1437b-tiff



940328Ae1437-pm4

940328Ae1437a-tiff

Toggle Grip Design




Computer Test Panel

CREEP TEST PANEL


0

.0500

Load / Stress



Time Dependent Strain




2.0 min
1.0 min
30 sec
10.0 sec
5.0 sec
2.0 sec
.5 sec

0

Rate

Data Rate



Temperature



Start Test

0

Time




Experimental Procedure

- **Cast, Cut and Measure Samples**
- **Material Tester Calibration**
- **Perform Modulus Tests on Kapton Polyimide**
- **Perform Modulus Tests on 6FDA + APB Polyimide**
- **Perform CTE Tests on 6FDA + APB Polyimide**
- **Tabulate and Graph Results**
- **Compare Results to Material Source Data**




Modulus of Elasticity Results


.5 mil Kapton Type H Linear Curve Fit



6FDA+APB Polyimide Linear Curve Fit



Comparison of Stress vs. Strain Curves for the 6FDA+APB Polyimide






Modulus of Elasticity Results cont.

	Manufacturer's Data	Harris / NASA	Results of Tests	% Difference
Kapton Type H	430,000 psi 1 mil at 25 °C		467,830 psi .5 mil at 23 °C	8.8 %
6FDA + APB		426,000 psi 452,000 psi	457,500 psi 457,500 psi	7.5 % 1.3 %



Coefficient of Thermal Expansion Results

6FDA+APB Polyimide CTE






Coefficient of Thermal Expansion Results cont.

Average CTE	Harris Data	Results of Tests	% Difference
	27.2E-6 in/(in°F)	25.7E-6 in/(in°F)	5.7%



Conclusions and Recommendations

- All Tests Showed Good Repeatability
- Results Compared Favorably to Source Data
- Values Presented here may be used as Design Parameters for Applications of Thin Films in Solar Thermal Propulsion
- The Determination of other Material Properties is Recommended
- Further Investigation of the Non-linearity in the CTE Curve is Recommended



Acknowledgements

- Phillips Laboratory, Edwards Air Force Base, California
 - Ms. Kristi K. Laug
- SRS Technologies, Huntsville, Alabama
 - Mr. Paul A. Gierow
- NASA LaRC, Langley, Virginia
 - Ms. Anne St. Clair